

Technical Data Sheet

To DIN EN ISO, Marks & Spencer Standards

Febr. 2007

| Article Name | FS No. 35 | | | |
|--------------------------|--|--|--|--|
| Article Description | Metallic Embroidery Thread | | | |
| Composition | 60% polyamid 40% metallised polyesterfoil | | | |
| Harmonised Tariff Number | 560500000 | | | |
| Count | 270 dtex 240 den ca. 37.040 m / kg | | | |
| Make Up Available | 5000 m cone | | | |

Fastness Rating – Scale 1 (worst) – 5 (best)

| Fastness to washing at 60°C DIN EN 20105 / M & S C4A | 4-5 |
|--|-----|
| Fastness to water (damp for 4hrs at 37°C) DIN EN ISO 105-E01 / M & S C6 | 4-5 |
| Fastness to rubbing dry (10 rubs on dry white Fabric) DIN EN ISO 105-X12 / M & S C8 | 4 |
| Fastness to rubbing wet (10 rubs on wet white Fabric) DIN EN ISO 105-X12 / M & S C8 | 3-4 |
| Fastness to dry cleaning DIN EN ISO 105-D01 | 4-5 |

Fastness Rating - Scale 1 (worst) – 8 (best)

| Fastness to light (100hrs xenon light) DIN EN ISO 105-B02 | | | | | 6-7 Due to different dye stuffs not applicable to all colors. |
|--|--|--|--|--|--|
| | | | | | |

Mechanical-Technological Values

| Tensile Strength cN (force until thread breaks, in Centinewton) DIN EN ISO 2062 | approx. 650 | | | | |
|---|---------------|--------------|--|---|--|
| Elongation (% of stretch extension with weight tension until breaks) DIN EN ISO 2062 | approx. 30-35 | | | | |
| Recommendations for care | 60°C | \bigotimes | | P | |
| Color Card No. | 59 | | | | |

dtex = decitex = weight in grams of 10,000m of yarn; den = denier = weight in grams of 9,000m of yarn 1 denier = 1,111 decitex; 1 Centinewton = slightly more than 1 gram dtex x 2 = two-ply of yarn; den x 2 = two-ply of yarn

